

Product	VISIBLE LIGHT		UV Rejection	SOLAR ENERGY			Thickness	IR REJECTION		Shading Coefficient	TSER
	Transmittance VLT	Reflectance VLR ext / int		Transmittance	Reflectance	Absorbance		900~1,000nm	780~2,500nm		
CAMO 12	12%	6% / 5%	99%	7%	5%	88%	1.5 Mil	97%	98%	0.41	71%
CAMO 32	32%	6% / 6%	99%	18%	5%	77%	1.5 Mil	96%	98%	0.50	66%
SHURE X 06	6%	6% / 5%	99%	4%	5%	91%	1.5 Mil	97%	96%	0.39	71%
SHURE X 12	12%	5% / 5%	99%	9%	5%	86%	1.5 Mil	95%	95%	0.44	65%
SHURE X 20	20%	5% / 5%	99%	11%	5%	84%	1.5 Mil	97%	97%	0.44	63%
SHURE X 32	32%	5% / 5%	99%	21%	5%	74%	1.5 Mil	95%	95%	0.54	58%
SHURE X 50	52%	6% / 7%	99%	28%	5%	67%	1.5 Mil	95%	95%	0.59	57%
SANTANA 06	6%	6% / 5%	99%	10%	5%	85%	1.5 Mil	92%	91%	0.43	69%
SANTANA 12	13%	6% / 5%	99%	10%	5%	85%	1.5 Mil	92%	95%	0.44	68%
SANTANA 22	22%	6% / 5%	99%	15%	5%	80%	1.5 Mil	94%	95%	0.47	62%
SANTANA 32	32%	6% / 6%	99%	22%	5%	73%	1.5 Mil	91%	93%	0.53	57%
OPTIC W 05	5%	6% / 5%	99%	11%	5%	84%	1.5 Mil	82%	92%	0.44	62%
OPTIC W 15	13%	6% / 5%	99%	13%	5%	82%	1.5 Mil	81%	94%	0.46	60%
OPTIC W 35	33%	6% / 5%	99%	23%	5%	72%	1.5 Mill	85%	94%	0.54	56%

Product	VISIBLE LIGHT		UV Rejection	SOLAR ENERGY			Thickness	IR REJECTION		Shading Coefficient	TSER
	Transmittance VLT	Reflectance VLR ext / int		Transmittance	Reflectance	Absorbance		900~1,000nm	780~2,500nm		
RODE 05	5%	5% / 5%	99%	11%	5%	84%	1.5 Mil	81%	94%	0.46	64%
RODE 15	14%	5% / 5%	99%	15%	5%	80%	1.5 Mil	81%	91%	0.49	60%
RODE 35	38%	5% / 5%	99%	27%	6%	67%	1.5 Mil	80%	91%	0.59	52%
RODE 50	52%	7% / 7%	99%	35%	5%	60%	1.5 Mil	80%	90%	0.65	47%
FORET 05	5%	5% / 5%	99%	13%	5%	82%	1.5 Mil	81%	90%	0.45	61%
FORET 15	15%	6% / 6%	99%	19%	5%	76%	1.5 Mil	77%	90%	0.48	58%
FORET 35	33%	6% / 6%	99%	36%	5%	59%	1.5 Mil	63%	84%	0.59	49%
FORET 50	50%	6% / 6%	99%	45%	5%	50%	1.5 Mil	55%	80%	0.69	43%
PENDER S 06	6%	5% / 6%	99%	12%	5%	83%	1.5 Mil	81%	89%	0.44	61%
PENDER S 12	11%	5% / 6%	99%	15%	5%	80%	1.5 Mil	77%	90%	0.47	59%
PENDER S 32	31%	6% / 6%	99%	31%	5%	64%	1.5 Mil	62%	84%	0.59	48%
PENDER S 80	84%	6% / 7%	99%	63%	6%	31%	1.5 Mil	53%	54%	0.84	27%
PENDER 05	6%	5% / 5%	99%	15%	5%	80%	1.5 Mil	72%	85%	0.48	59%
PENDER 15	14%	5% / 5%	99%	20%	5%	75%	1.5 Mil	70%	87%	0.52	55%
PENDER 35	33%	5% / 5%	99%	37%	5%	58%	1.5 Mil	55%	83%	0.65	46%
PENDER 50	54%	7% / 7%	99%	48%	6%	46%	1.5 Mil	46%	79%	0.73	41%

Product	VISIBLE LIGHT		UV Rejection	SOLAR ENERGY			Thickness	IR REJECTION		Shading Coefficient	TSER
	Transmittance VLT	Reflectance VLR ext / int		Transmittance	Reflectance	Absorbance		900~1,000nm	780~2,500nm		
AURA 10	13%	20% / 11%	99%	7%	20%	73%	2 Mil	98%	98%	0.36	76%
AURA 25	25%	14% / 12%	99%	13%	13%	74%	2 Mil	97%	96%	0.43	70%
REINEY BLUE 10	11%	17% / 11%	99%	11%	20%	69%	2 Mil	88%	96%	0.38	71%
REINEY BLUE 25	25%	15% / 14%	99%	23%	17%	60%	2 Mil	80%	92%	0.48	65%
BACH 10	11%	18% / 9%	99%	12%	24%	64%	2 Mil	85%	95%	0.38	67%
BACH 25	23%	15% / 12%	99%	21%	19%	60%	2 Mil	78%	91%	0.46	60%
HANDEL 10	12%	23% / 9%	99%	12%	28%	60%	2 Mil	86%	95%	0.37	68%
HANDEL 25	23%	18% / 11%	99%	20%	20%	60%	2 Mil	79%	92%	0.46	60%
SUNSET R 06	6%	19% / 8%	99%	9%	21%	70%	1.5 Mil	90%	89%	0.36	69%
SUNSET R 10	10%	16% / 7%	99%	16%	16%	68%	1.5 Mil	85%	79%	0.44	65%
SUNSET R 22	22%	17% / 9%	99%	25%	14%	61%	1.5 Mil	78%	75%	0.51	62%
SUNSET R 30	28%	16% / 7%	99%	27%	17%	56%	1.5 Mil	77%	77%	0.53	59%
SUNSET Q 10	11%	15% / 11%	99%	13%	20%	67%	1.5 Mil	82%	85%	0.39	64%
SUNSET Q 25	24%	15% / 10%	99%	26%	17%	57%	1.5 Mil	76%	81%	0.50	62%